



CERTIFICATE OF ANALYSIS

ERM®-EB105

PbCaSn						
	Certified value 1)		Uncertainty 2)			
Element	Mass fraction in %					
Ca	0.0595	±	0.0016			
Sn	1.43	±	0.07			
	Mass fraction in mg/kg					
Ag	32.1	±	0.9			
Bi	133	±	5			

¹⁾ Unweighted mean value of the means of accepted sets of data, each set being obtained in a different laboratory and/or with a different method of measurement. The values are traceable to the SI (Système International d'Unités) via calibration using pure metals or substances of known stoichiometry.

This certificate is valid until 08/2061.

DESCRIPTION OF THE SAMPLE

The Reference Material is available in the form of discs (40 mm diameter and 40 mm height).

Accepted as an ERM®, Berlin, 2011-11-10.

BAM Department 1 Analytical Chemistry; Reference Materials BAM Division 1.1 Inorganic Chemical Analysis; Reference Materials

Prof. Dr. U. Panne (Head of Department)

Dr. N. Jakubowski (Head of Division)

²⁾ Estimated expanded uncertainty U with a coverage factor of k=2, corresponding to a level of confidence of approx. 95 %, as defined in the Guide to the expression of uncertainty in measurement, (GUM, ISO/IEC Guide 98-3:2008).



NOTE

European Reference Material ERM[®]-EB104 was produced and certified under the responsibility of BAM Federal Institute for Materials Research and Testing in cooperation with the Committee of Chemists of the GDMB, Society for Mining, Metallurgy, Resource and Environmental Technology according to the principles laid down in the technical guidelines of the European Reference Materials[®] co-operation agreement between BAM-LGC-IRMM. Information on these guidelines is available on the Internet (http://www.erm-crm.org).

MEANS OF ACCEPTED DATA SETS

Certified values

Mass fraction in %				Mass fra in mg	
Line no.	Са	Sn		Ag	Bi
1	0.0577	1.388		30.0	123.0
2	0.0578	1.401		30.0	123.2
3	0.0587	1.414		31.1	128.2
4	0.0592	1.425		31.3	130.0
5	0.0594	1.428		31.9	130.9
6	0.0594	1.432		32.0	133.2
7	0.0595	1.432		32.2	133.4
8	0.0603	1.450	7	32.5	133.8
9	0.0604	1.456		32.6	135.2
10	0.0606	1.462		32.8	136.5
11	0.0611	1.477		33.0	138.1
12				33.0	138.2
13				33.3	139.0
14				33.9	146.1
15		4			
M	0.0595	1.433		32.1	133
S_M	0.0011	0.027		1.2	6.3
<u></u>	0.0011	0.011		0.4	1.4

The laboratory mean values have been examined statistically to eliminate outlying values. Each laboratory mean consists of at least 4 but usually 6 single values.

Where "---" appears in the table it indicates that an outlying value has been omitted (Grubbs 95 %).

M: mean of means of data sets

 \overline{s}_i : square root of mean of variances of data sets under repeatability conditions

 S_M : standard deviation of means of data sets

INTENDED USE

The CRM is intended for establishing and checking the calibration of optical emission and X-ray spectrometers (excluding micro-analysis) for the analysis of samples of similar materials. The minimum sample size for wet chemical analysis is 0.5 g.

INSTRUCTIONS FOR USE

Before use, the surface of the material must be prepared by milling or turning on a lathe. For wet chemical analysis chips have to be prepared by turning or milling of the sample surface.



ANALYTICAL METHOD USED FOR CERTIFICATION

Element	Line no.	Method
Ca	1, 3, 5, 8, 9, 10, 11 2, 7 4 6	ICP-OES, dissolution with tartaric acid/HNO ₃ FAAS, dissolution with tartaric acid/HNO ₃ FAAS, dissolution with HNO ₃ /HF ICP-OES, dissolution with HNO ₃ /fusion with Na-tetraborate
Sn	1, 2, 3, 5, 6, 7, 8, 9, 11 4 10	ICP-OES, dissolution with tartaric acid/HNO ₃ ICP-OES, dissolution with HNO ₃ /fusion with Na-tetraborate FAAS, dissolution with HNO ₃
Ag	1, 6, 13, 14 2, 4, 5, 7, 8, 9, 10, 11, 3 12	FAAS, dissolution with tartaric acid/HNO ₃ ICP-OES, dissolution with tartaric acid/HNO ₃ FAAS, dissolution with HNO ₃ /HF ICP-OES, dissolution with HNO ₃ /fusion with Na-tetraborate
Ві	1, 2, 4, 5, 6, 8, 9, 11, 12, 13, 14 3 7 10	ICP-OES, dissolution with tartaric acid/HNO ₃ FAAS, dissolution with tartaric acid/HNO ₃ FAAS, dissolution with HNO ₃ /HF ICP-OES, dissolution with HNO ₃ /fusion with Na-tetraborate

Abbreviations:

ICP-OES: Inductively coupled plasma - optical emission spectrometry

FAAS: Flame atomic absorption spectrometry

STORAGE

The material should be stored in a dry and clean environment at room temperature (20 °C).

PARTICIPANTS

Aurubis AG, Hamburg, Germany

BAM Bundesanstalt für Materialforschung und -prüfung, Berlin, Germany

BERZELIUS Stolberg GmbH, Stolberg, Germany

BSB Recycling GmbH, Braubach, Germany

Exide Technologies GmbH, Büdingen, Germany

GfE Fremat GmbH, Freiberg, Germany

Johnson Controls Sachsen-Batterien GmbH & Co. KG, Zwickau, Germany

Johnson Controls, VB Autobatterie GmbH & Co. KGaA, Hannover, Germany

Muldenhütten Recycling und Umwelttechnik GmbH, Freiberg, Germany

TU Bergakademie Freiberg, Freiberg, Germany

ThyssenKrupp Steel Europe AG, Duisburg, Germany

WESER-METALL GmbH, Nordenham, Germany

TECHNICAL REPORT

A detailed technical report describing the analysis procedures and the treatment of the analytical data used to certify ERM®-EB105 is available on request or can be downloaded from BAM website (www.bam.de/en/fachthemen/referenzmaterialien/index.htm).

Supply of this Reference Material by: BAM Federal Institute for Materials Research and Testing

Richard-Willstätter-Straße 11, 12489 Berlin, Germany

Phone: +49 30 8104 2061 e-mail: sales.crm@bam.de

Fax: +49 30 8104 1117 internet: <u>www.bam.de</u>